

SECURITY INFORMATION  
CENTRAL INTELLIGENCE AGENCY  
Approved For Release 2002/08/08 : CIA-RDP82-00457R012800200005-7  
**INFORMATION REPORT**

REPORT N  
CD NO.

25X1A  
*[Handwritten mark]*

CONTRY German (Russian Zone)

DATE DISTR. 16 July 1952

SUBJECT The Lauchhammer Coke Manufacturing Project

NO OF PAGES 2

PLACE 25X1A

NO. OF ENCL.  
(LISTED BELOW)

ACQUIRED [REDACTED]

SUPPLEMENT TO 25X1X  
REPORT NO.

DATE OF INFO. [REDACTED]

--	--

1. The report deals with the DDR project of producing hard coke from lignite in a plant at Lauchhammer. The information is taken from a copy of a summary report classified "strictly confidential" which refers to research project No. 510232/3026 of the DDR Zentralamt für Forschung und Technik (ZFT).
2. The project seeks to produce a hard coke as a substitute for bituminous coke in metallurgy, according to a process developed by Dr. Pilkenroth and Dr. Rummel. In order to obtain coke which is firm and low in ash and sulfur content, coal of low tar, sulfur and ash content is made into very fine-grain briquettes. The size of the grain should be no larger than 0-1 mm. Experiments showed that the content of fine material in the granular size of 0-0.5 mm must account to at least 50 percent of the total granulation. It is important that the moisture content in the various granular fractions be largely the same; otherwise, shrinkage strains will appear during the coking process which will loosen up the texture considerably. This coal is made into briquettes in extruding presses without addition of a binding agent; the briquettes have a solidity of 200-210 kg/cm<sup>2</sup>. Before the briquettes are placed into the vertical chamber furnaces, however, they are subjected to a drying process under 2000-3000° C., in order to prevent a loosening up of the briquette texture by sudden water condensation in the coking furnaces. Thereafter, the briquettes are coked in the usual way at a temperature of 1150°-1200° C. The coke is allowed to refine for a period of 16 hours before it is drawn off.

3. (a) Analysis data of the processed coal:

Moisture content	56-58%
Sulfur "	0.5-0.7%
Tar "	3-5%
Fischer analysis)	
Combustion heat	2000 kcal/kg
Ash content	5-7%

- (b) Analysis data of the briquettes:

Moisture content	10-12%
Density	1.32 g/cm <sup>3</sup>
Compressive strength	230 kg/cm <sup>2</sup>

CLASSIFICATION SECRET

STATE	ARMY	NAVY	AIR	NSRB	DISTRIBUTION						
	X	X	X	X							

(c) Properties of the coke obtained from lignite at the trial plant in Delitzsch:

Moisture content	5-10%
Ash content (ref. to anhydrous coke)	12-13%
Sulfur " ( " " " )	1.1-1.4%
Volatile content (" " " )	3-5%
Lower heating value	6200-6500 kcal/kg
Igniting point acc. to Bunte and Kölmel	450 degrees
Compressive strength (varied depending on the briquette material)	120-180 kg/cm <sup>2</sup>
Abrasion strength ( " " " )	40-65%
Drop strength ( " " " )	65-80%
Porosity	greater than 40 mm 20-25%

(d) Composition of the water and ash free coke:

Carbon	98.75%
Hydrogen	0.75%
Oxygen + nitrogen + organic sulfur	0.70%

(e) The following grades and percentages were obtained:

Larger than 30 mm	65-80%
30-10 mm	20-10%
Smaller than 10 mm	19-15%